



Technical Information

Product name	: MoTip Kompakt Car Lacquer	
Colours	: Non Metallic	Metallic
Article number	: 41000 through 46999	51000 - 56000
Supplier / Producer	: MOTIP DUPLI B.V.	
	Wolfraamweg 2	
	NL-8471 XC WOLVEGA	
	Telephone number	+31 561 – 69 44 00
	Telefax number	+31 561 – 69 44 31

Product description

High quality car repair lacquer to repair and embellish car parts in the original car colour.

Product characteristics

Original car colour
Fast drying
Excellent coverage and filling property
Lasting colour and gloss
Scratch free and shock proof
Resistant to weather influences
UV resistant and non-fading
Corrosion preventive
Excellent adhesion

Physical and Chemical Characteristics

Contents	: 400 ml
Base	: Acrylic resin
VOC-content	: Approximately 88% w/w
Solid content	: Approximately 12% w/w
Coverage	: 1,25 to 1,75 m ²
Dust dry	: After 5 to 10 minutes
Tack free	: After 10 to 20 minutes
Hardened/re-sprayable	: After 2 hours
Heat resistant	: To 110°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol. For an optimum result, apply a finishing layer of acrylic clear varnish.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.